

CE

FMC-GR

FOUSEKIS MARBLE CONSULTING P.C.

NEAS ELBETIAS 2, 16232 BYRONAS ATTICA GREECE

EN 1469: SLABS FOR CLADDING

EN 12058: SLABS OF NATURAL STONE FOR FLOOR AND STAIRS

EN 12057: MODULAR TILES

NATURAL STONE: POLARIS

LIST OF CHARACTERISTICS	Declared Values	TEST METHOD
APPARENT DENSITY	2770kg/m ³	EN 1936
ABSORPTION COEFFICIENT	0,23%wt	EN 1936
COMPRESSION STRENGTH	990kg/cm ²	EN 1936
MODULUS OF RUPTURE	132kg/cm ²	EN 1936
ABRASION RESISTANCE (after 1000m)	6,58mm	EN 1936
MICROHARDNESS KNOOP	321,6kg/mm ²	EN 1936

MINERALOGICAL COMPOSITION

CALCITE	8%
DOLOMITE	90%
QUARTZ	2%